

## Verdcol® Yellow 110 PTR

- Transparent and red shade yellow
- Good durability

<b>Colour Index</b>	Pigment Yellow 110
<b>C.I. No.</b>	56280
<b>CAS No.</b>	5590-18-1
<b>REACH Pre-Registration No.</b>	Available on Request

<b>Physical Data</b>	
Density[g/cm <sup>3</sup> ]	1.8-1.9
Specific Surface [m <sup>2</sup> /g]	45-55
Oil Absorption[g/100g]	45-50
Heat Stability[°C]	220°C

<b>Application</b>	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



**Full Shade**



**Tint 1:25 TiO2**

<b>Fastness</b>						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7-8	4-5	5	5	4	4	4-5

For more details, please contact [service@verdcol.com](mailto:service@verdcol.com)