

Verdcol[®] Red 177

- Transparent blue shade red
- Excellent fastness


Colour Index	Pigment Red 177
C.I. No.	65300
CAS No.	4051-63-2
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.4~1.5
Specific Surface [m ² /g]	110~115
Oil Absorption[g/100g]	60~65
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	4~5	5	5	4~5	4~5	4~5

For more details, please contact service@verdcol.com