

## Verdcol® Scarlet 166

- Mid shade red
- Recommended for fibre coloration

<b>Colour Index</b>	Pigment Red 166
<b>C.I. No.</b>	20730
<b>CAS No.</b>	3905-19-9
<b>REACH Pre-Registration No.</b>	Available on Request

### Physical Data

Density[g/cm <sup>3</sup> ]	1.4-1.5
Specific Surface [m <sup>2</sup> /g]	25-30
Oil Absorption[g/100g]	50-55

### Application

PVC	●
PE/PP	●
PS	●
ABS	○
PA	-
PC	○
PUR	○
PET/PBT	○
Rubber	○
● : recommended	
○ : limited suitability	
- : not recommended	

### Fastness

Light	Weather	Migration (In PVC)	Acid	Alkali
7-8	4-5	4-5	5	5




**Full Shade**



**Tint 1:10 TiO<sub>2</sub>**

### Heat Resistance ( In HDPE)



For more details, please contact [service@verdcol.com](mailto:service@verdcol.com)