

Verdcol® BML Yellow 151 GH

- Green shade yellow
- Relatively good opaciy
- Good color strength
- Recommended as replacement for diarylide and lead chromate

Colour Index	Pigment Yellow 151
C.I. No.	13980
CAS No.	31837-42-0
REACH Pre-Registration No.	Available on Request

Physical Data

Density[g/cm ³]	1.5~1.6
Specific Surface [m ² /g]	20~23
Oil Absorption[g/100g]	45~50

Application

PVC	●
PE/PP	●
PS	-
ABS	-
PA	-
PC	-
PUR	-
PET/PBT	-
Rubber	-

● : recommended

○ : limited suitability


- : not recommended

Fastness

Light	Weather	Migration (In PVC)	Acid	Alkali
8	4-5	5	5	3




Full Shade



Tint 1:10 TiO₂

Heat Resistance (In HDPE)



For more details, please contact service@verdcol.com