

Verdcol® Orange 43

- Pure shade orange with good colour strength
- Good fastness


Colour Index	Pigment Orange 43
C.I. No.	71105
CAS No.	4424-06-0
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.5-1.6
Specific Surface [m ² /g]	35-40
Oil Absorption[g/100g]	80-85
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	○
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7-8	3-4	5	5	4-5	4-5	4-5

For more details, please contact service@verdcol.com