

Verdcol[®] Violet 19 B2

- **Highly saturated violet**
- **High transparency and gloss**
- **High colour strength**


Colour Index	Pigment Violet 19
C.I. No.	73900
CAS No.	1047-16-1
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.4~1.5
Specific Surface [m ² /g]	75~80
Oil Absorption[g/100g]	80~90
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	4~5	5	5	4~5	4~5	5

For more details, please contact service@verdcol.com