

Verdcol® Scarlet 166

- Mid shade red with good opacity
- Good fastness

Colour Index	Pigment Red 166
C.I. No.	20730
CAS No.	3905-19-9
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.4-1.5
Specific Surface [m ² /g]	25-30
Oil Absorption[g/100g]	50-55
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7-8	4-5	5	5	4-5	4-5	4

For more details, please contact service@verdcol.com