

Verdcol® DPP Red 254 PTR

- Bright and highly saturated mid shade red
- Good fastness


Colour Index	Pigment Red 254
C.I. No.	56110
CAS No.	84632-65-5
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.5-1.6
Specific Surface [m ² /g]	28-32
Oil Absorption[g/100g]	45-50
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	4~5	5	5	5	5	5

For more details, please contact service@verdcol.com