

Verdcol® Yellow 191 C

- Economical red shade yellow
- Excellent general properties
- Recommended as replacement for diarylide and lead chromate

Colour Index	Pigment Yellow 191
C.I. No.	18795
CAS No.	129423-54-7
REACH Pre-Registration No.	Available on Request

Physical Data


Density[g/cm ³]	1.7~1.8
Specific Surface [m ² /g]	20~25
Oil Absorption[g/100g]	60~65



Full Shade

Application

PVC	●
LDPE	●
HDPE/PP	●
PS	●
ABS	●
PA	○
PC	○
PUR	●
PET/PBT	○
RUBBER	●
● : recommended	
○ : limited suitability	
- : not recommended	




Tint 1:10 TiO₂

Fastness

Light	Weather	Migration (In PVC)	Acid	Alkali
7	3~4	5	5	5

Heat Resistance (In HDPE)



For more details, please contact service@verdcol.com