

## Verdcol<sup>®</sup> Blue 60 HG

- Highly saturated red shade blue
- Good fastness


<b>Colour Index</b>	Pigment Blue 60
<b>C.I. No.</b>	69800
<b>CAS No.</b>	81-77-6
<b>REACH Pre-Registration No.</b>	Available on Request

Physical Data	
Density[g/cm <sup>3</sup> ]	1.4-1.5
Specific Surface [m <sup>2</sup> /g]	40-45
Oil Absorption[g/100g]	40-45
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO<sub>2</sub>

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7-8	4-5	5	5	5	5	5

For more details, please contact [service@verdcol.com](mailto:service@verdcol.com)