

Verdcol® Red 144

- Mid-blue shade red
- Good fastness to light and weather


Colour Index	Pigment Red 144
C.I. No.	20735
CAS No.	5280-78-4
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.4~1.5
Specific Surface [m ² /g]	30~35
Oil Absorption[g/100g]	60~65
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7~8	4	5	5	4	3~4	4

For more details, please contact service@verdcol.com